

07.08.2008

JT20-Y0203 DF Base Clear

- Specifications : Two-part reaction base clear ink for insert forming
- Usage : Base clear for VIC(N),MP4,MP4 Slow Dry-series.
- Mixing ratios : Add D-Hardener to main agent at the ratio of 1 : 10, and agitate them well before use.
- Pot life : 4~6 hours at 20°C
- Diluent : T-912
- Drying time : 80°C x 20min.
- Mesh : T-250 mesh per/inch fabric
- Wash Up : T-15