

June 20,2003

MP4 SLOW DRY INK SERIES

The MP4 slow dry ink series is newly developed for Insert on polycarbonate materials. They are Two-part reaction ink system. They feature outstanding flexibility (resistance to stamping, bending, embossing) and resistance against heat.

Specifications

| | |
|----------------|---|
| Ink type: | Two part reaction ink consisting of polyester resin-based ink main agent and special hardener |
| Usage: | Insert ink for polycarbonate material |
| Finish: | Gloss finish |
| Drying time: | 80°C x 20 minutes |
| Mixing ration: | Main agent : D-hardener = 100 : 3 *Pot life is about 6~8 hours after mixing with hardener |
| Diluent: | T-980 (standard solvent) |
| Wash up: | T-31 Solvent |